textiletechnology

LEEDAZIL H180

Silicon softner

Characteristics

Type of productmicro emulsion from aminosiloxanIonogenitynonionicAppearancecoulerless and transparentConsistencyliquidPH4

Properties

- Extremely soft handle
- Stable in front of washing
- Hydrofoil silicon softner
- Improve the sewing property of the fabric
- Increase the elastic effect specially for tricot fabric
- Useable for towel and bedsheet
- For permanent finishing for cotton, viscose, wool ,synthetic fibers and blending of them in continues and discontinues methods

Application

LeedazilH180 dissolving in water with any ratio and have a transparent and colourless emulsion.Itcan used for folard and exhaust process.

- Exhaust Process

Leedasil H180	: 1-3
Temperature	: $40 - 45^{\circ c}$
Time	: 20 – 30 min
PH	: 5

- Folard system

LeedasilH1	80:	5 - 30	g/l
PH	:	5	
Drying	:	130 °C	,

Spesial remarks

Storage stabilityat least 9 monthsPreservation it from frost.keep it at $20 \,^{\circ}c$.

