



LEEDAZIL H300

Silicon softner

Characteristics

Type of product	micro emulsion from aminosiloxan
Ionogenity	nonionic
Appearance	coulerless and transparent
Consistency	liquid
PH	4

Properties

- Extremely soft handle
- Stable in front of washing
- Hydrofoil silicon softner
- Improve the sewing property of the fabric
- Increase the elastic effect specially for tricot fabric
- Useable for towel and bedsheet
- For permanent finishing for cotton, viscose, wool ,synthetic fibers and blending of them in continues and discontinues methods

Application

LeedazilH300 dissolving in water with any ratio and have a transparent and colourless emulsion.Itcan used for folard and exhaust process.

- Exhaust Process

Leedasil H300 : 1 – 3
Temperature : 40 – 45 °c
Time : 20 – 30 min
PH : 5

- Folard system

LeedasilH300: 5 – 30 g/l
PH : 5
Drying : 130 °c

Spesial remarks

Storage stability at least 9 months
Preservation it from frost.keep it at 20 °c .