textiletechnology

LEEDAZIL SE28

Silicon softener

Characteristics

Type of productmicro emulsion from aminosiloxanIonogenitynonionicAppearancecolorless and transparentConsistencyliquidPH5

Properties

- Extremely soft handle
- Stable in front of washing
- Hydrofoil silicon softner
- Improve the sewing property of the fabric
- Increase the elastic effect specially for tricot fabric
- Useable for towel and bedsheet
- For permanent finishing for cotton, viscose, wool ,synthetic fibers and blending of them in continues and discontinues methods

Application

Leedazil SE28 dissolving in water with any ratio and have a transparent and colorless emulsion. It can used for folard and exhaust process.

- Exhaust Process Leedasil SE28 : 0.7 – 2

Temperature : $40 - 45^{\circ c}$ Time : 20 - 30 min PH : 5

- Folard system

Leedasil SE28 : 3.5 – 22 g/l PH : 5 Drying : 130

Spesial remarks

Storage stabilityat least 9 monthsPreservation it from frost .keep it at $20 \,^{\circ}c$.

