textiletechnology

LEEDAZIL SE45

Silicon softner

Characteristics

Type of productmicro emulsion from aminosiloxanIonogenitynonionicAppearancecolorless and transparentConsistencyliquidPH5

Properties

- Extremely soft handle
- Stable in front of washing
- Hydrofoil silicon softner
- Improve the sewing property of the fabric
- Increase the elastic effect specially for tricot fabric
- Useable for towel and bedsheet
- For permanent finishing for cotton, viscose, wool ,synthetic fibers and blending of them in continues and discontinues methods

Application

Leedazil SE45 dissolving in water with any ratio and have a transparent and colorless emulsion .It can used for folard and exhaust process.

Exhaust Process				
Leedasil SE45	:	0.7 -	- 2	
Temperature	:	40 -	45	°c
Time	:	20 -	30	min
PH	:		5	
	Leedasil SE45 Temperature Time	Leedasil SE45 : Temperature : Time :	Leedasil SE45 : 0.7 - Temperature : 40 - Time : 20 -	Leedasil SE45 : $0.7 - 2$ Temperature : $40 - 45^{\circ}$ Time : $20 - 30^{\circ}$

- Folard system

Leedasil SE45 : 3.5 – 22 g/l PH : 5

Drying : 130

Spesial remarksStorage stabilityat least 9 monthsPreservation it from frost .keep it at $20 \,^{\circ}c$.

